JW-HD120N N-type Bifacial Mono Module

375-395W







IEC61215(2016), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System | ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



10-30% Additional Power Generation

30 years lifespan brings 10-30% additional power generation comparing with conventional P-type module



ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



Higher Reliability

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



Better Weak Illumination Response

Higher power output even under low-light environments like on cloudy or foggy days



Better Temperature Coefficient


Higher power generation under working conditions, thanks to passivating contact cell technology



Wider Applicability

More application scenes like BIPV, vertical installation, snowfield, high-humid, windy and dusty area

Linear Performance Warranty



^{*}Subject to the terms and conditions contained in the applicable Jolywood Solar Limited Warranty Statement. Also this 25

Electrical Properties	STC*				
Testing Condition	Front Side				
Peak Power (Pmax) (W)	375	380	385	390	395
MPP Voltage (Vmp) (V)	34.7	34.9	35.1	35.3	35.5
MPP Current (Imp) (A)	10.81	10.89	10.97	11.05	11.13
Open Circuit Voltage (Voc) (V)	41.6	41.8	42.0	42.2	42.4
Short Circuit Current (Isc) (A)	11.45	11.54	11.62	11.69	11.77
Module Efficiency (%)	20.55	20.83	21.10	21.38	21.65

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties NOCT*					
Testing Condition	Front Side				
Peak Power (Pmax) (W)	284	288	292	296	299
MPP Voltage (Vmp) (V)	32.6	32.8	33.0	33.2	33.4
MPP Current (Imp) (A)	8.72	8.78	8.84	8.91	8.97
Open Circuit Voltage (Voc) (V)	39.8	40.0	40.1	40.3	40.5
Short Circuit Current (Isc) (A)	9.23	9.30	9.37	9.43	9.49

*NOCT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Operating Properties Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 25 Power Tolerance 0~+5W Bifaciality* 80% *Bifaciality=Pmaxrear (STC) /Pmaxfront (STC) , Bifaciality tolerance:±5%

Temperature Coefficient		
Temperature Coefficient of Pmax*	-0.300%/°C	
Temperature Coefficient of Voc	-0.250%/℃	
Temperature Coefficient of Isc	+0.045%/°C	
Nominal Operating Cell Temperature (NOCT)	42±2°C	


^{*}Temperature Coefficient of Pmax±0.03%/°C

Mechanical Properties	
Cell Size	166.00mm*83.00mm
Number of Cells	120pcs(12*10)
Module Dimension	1756mm*1039mm*30mm
Weight	23kg
Front / Rear Glass*	2.0mm/2.0mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized)


^{*}Heat strengthened glass

With Different Power Generation Gain(regarding 380W as an example)					
Power Gain (%)	Peak Power (Pmax) (W)	MPP Voltage (Vmp) (V)	MPP Current (Imp) (A)	Open Circuit Voltage (Voc) (V)	Short Circuit Current (Isc) (A)
10	410	34.9	11.75	41.8	12.44
15	426	34.9	12.18	41.8	12.89
20	441	35.0	12.61	41.9	13.34
25	456	35.0	13.04	41.9	13.79
30	471	35.0	13.47	41.9	14.24

Engineering Drawing (unit: mm



Characteristic Curves | HD120N-380



Packaging Configuration					
Packing Type	20'GP	40'GP	40'HQ		
Piece/Pallet		36			
Pallet/Container	6	13	26		
Piece/Container	216	468	936		

"The specification and key features described in this datashest may deviate slightly and are quaranteed. Due to ongoing innovation, R&D enhancement, Jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datashee which shall be duly incorporated into the binding contract made by the parties governing all which shall be duly incorporated into the binding contract made by the parties governing all the parties of the state of the parties of the parti



